



Traconed B.V. - Safety at Sea (int.) Tel  
Kleidijk 88  
3161 HJ Rhoon  
The Netherlands

: +31 10 501 90 40  
Fax : +31 10 501 42 50  
Email : [info@traconed.com](mailto:info@traconed.com)  
Website : [www.traconed.com](http://www.traconed.com)

IBAN : NL71 INGB 0693 3455 27  
SWIFT : INGBNL2A  
VAT : NL007154392B01  
K.v.K. : 24 163 163

# NON-Kinking Polyethylene floating line

## DATA SHEET SELENE PE BRAIDED ROPE Ø 8

|                          |                                                                                                                            |
|--------------------------|----------------------------------------------------------------------------------------------------------------------------|
| MATERIAL:                | 100% POLYETHYLENE MONOFILAMENT                                                                                             |
| DIAMETER:                | 8 mm                                                                                                                       |
| WEIGHT :                 | 22 gram/meter                                                                                                              |
| BREAKING LOAD:           | 600 Kg                                                                                                                     |
| TEMPERATURE RESTISTANCE: | -25 °C +93 °C                                                                                                              |
| MELTING POINT:           | 165 °C                                                                                                                     |
| SOFTENING POINT:         | 135 °C                                                                                                                     |
| ACID RESISTANCE:         | GOOD                                                                                                                       |
| ALCALI RESISTANCE:       | HIGH                                                                                                                       |
| SOLUBILITY:              | SOLUBLE IN CL-                                                                                                             |
| ABRASION RESISTANCE:     | VERY GOOD                                                                                                                  |
| STRETCHING:              | 18% at working load – 25% at 35% of breaking load                                                                          |
| ATTENTION:               | breaking load is valid for new product. Any damage or<br>Incorrect use may decrease the value.<br>All data are + or – 10 % |

